



## Chemical Resistance Guide

The data in the following tables was obtained from numerous sources in the industry. The information is based primarily on the immersion of unstressed strips in the chemicals at ambient temperature and, to a lesser degree, on field experience. The end user should be aware of the fact that actual service conditions will affect the chemical resistance. It should be noted in the following charts that the "A" rating does not mean or imply that material will perform within original specification. The chemical resistance table should be used for reference only. It is the ultimate responsibility of the end user to determine the compatibility of the chemical being used in his or her particular application. Contact Hayward for information on Eastar® products.

CHEMICALS	CPVC	PP	PTFE	PVC	PVC-GF (Fibertec™)	PVDF	Ultem® (GF 40%)	EPDM	FPM	Nitrile/Buna/N	Hastelloy® C	Monel®	18-8 SS	316 SS	416 SS	Titanium	CHEMICALS	CPVC	PP	PTFE	PVC	PVC-GF (Fibertec™)	PVDF	Ultem® (GF 40%)	EPDM	FPM	Nitrile/Buna/N	Hastelloy® C	Monel®	18-8 SS	316 SS	416 SS	Titanium	
Acetal Benzene		A				A	X	X									Acrylic Emulsions	X																
Acetal Oxide		A				B	X	C									Acrylonitrile	X	B	A	X	X	A		X	X	C	AB	A	A	A	A	A	
Acetaldehyde	X	B	A	X	X	C		B	X	X		A	A	A			Adipic Acid, Aq.	A	A	A	A	A	A		A	A	A	A	AB	A	A	A	A	
Acetaldehyde, Aq.	X	A	A	X	X	X	A	A	B		A	A	A	A	A		Air	A	A	A	A	A	A		A	A	A	A	A	A	A	A	A	
Acetamide		A	A				A	A	C	A	A			A	A		Alcohol	C	A						A	B	A	A	A	A	A	AC	AB	
Acetate Solv., Crude	X	X		X	X	A				A		A	A	B			Aldehyde			A					A	X	X							
Acetate Solv., Pure	X	X	A	X	X	A		C	X	X	A		A	A	A		Alkanes			A					X	A	A							
Acetic Acid 10%	A	A	A	A	A	A	B	X	B				A	A	B		Alkazene			A					X	B	X							
Acetic Acid 20%	B	A	A	A	A	A	B	C	B				A	B	A		Allyl Alcohol	X	A	A	X	C	A		A	B	A	A	A	A	A	A	A	
Acetic Acid 30%	B	A	A	A	A	A	A	C	B								Allyl Aldehyde		A						A	B								
Acetic Acid 5%	A	A	A				A	A	A	B							Allyl Bromide			A					B	X								
Acetic Acid 50%	B	A	A	A	A	A	B	C	A				A	C			Allyl Chloride	X	B	X	X	A			X	B	X	A		AB	A			
Acetic Acid 60%	B	B	A	A	A	A	C	C					A	X			Allyl Trichloride			A					A	X								
Acetic Acid 80%	B	C	A	B	C	A	B	C	C				A	X			Alum	A	A	A	A	A	A		A	A	A	A	AB	AC	AB	X	A	
Acetic Acid, Glacial	X	B	A	X	C	B	C	B	X	X			A	X	B		Aluminum Acetate	A	A						A	C	B	A	AC	A	AB	AC	A	
Acetic Aldehyde			A				A	X	X								Aluminum Bromide	A							A	A	A							
Acetic Anhydride	C	B	A	X	X	B		C	X	C	A		AB	A	X	B	Aluminum Chloride	A	A	A	A	A	A		A	A	A	A		X	X	X	AB	
Acetic Ester			A				B	X	X								Aluminum Fluoride	A		A	C	A			A	A	A	AB	A	X	C	X	A	
Acetic Ether			A				B	X	X								Aluminum Formate	A							X	X								
Acetol			A														Aluminum Salts	A	A	A	A	A	A		A	A	A						X	X
Acetone	X	B	A	X	X	X	C	A	X	C	A		A	A	AB	A	Aluminum Sulfate	A	A	A	A	A	A		A	A	A			B	X	A		
Acetonitrile			B	A	X	X	A	C	A	C	C		A	A	AB		Amber Acid	A	A	A	A	A	A		A	A								
Acetophenone	X	A	A	X		A		A	X	C			A	A	X		Amines	X	A	C	C	B			X	X	AB	A	A	A	A	AB		
Acetyl Acetone	X		A	X	X	X		A	X	X			A		AB		Ammon. Metaphosph.	A	A	A	A	A	A		A	A	A							
Acetyl Bromide			A			A											Ammonia 10%	X	A	A	A	A			A	X			A	A	A			
Acetyl Chloride	X	A	A	X	X	A		X	C	C			BC	AC	AB		Ammonia, Anhydrous	X	A	A	X	X	B		A	X	C	A	AB	A	A	AB		
Acetyl Propane			A				B	X	X								Ammonia, Aq. 25%	A	A		A	A	A								B			
Acetylene Dichl.			A					A					X				Ammonia, Dry Gas	A	A	A	A	A			A	X	A		A	A	A			
Acetylene Tetrachl.			A				X	A	X	A		A	A	A			Ammonia, Liquid	X	A	A	X	X	A	C	A	X	B	A	A	AB	A	A	AB	
Acetylene	C	A	A	C	C	A		A	A	A	A		A	A	A		Ammonia, Nitrate	B	A	B	C	A			A	A	B							
Acid Mine Water	A	B	A	A	A	A		A									Ammonium Acetate	A	A	A	A	A			A	A	A	A	A	A	X			
Acrylic Acid	X	A	X	X	A					A							Ammonium Alum	X	A	A	X	C	A		A	A	B	BC	A	A	A			

A = Excellent, no effect • B = Good, minor effect • C = Fair, data not conclusive, testing recommended • X = Not recommended.

Ratings are based on testing at an ambient temperature of 70°F. The chemical resistance table is for reference only. End users should test to determine application suitability. Butterfly valves, Solenoid valves, Diaphragm valves and all other valves with elastomers fully exposed to process media should derate elastomer scores by one level (i.e. "B" becomes "C", "C" becomes "X").

# Chemical Resistance Guide, CONTINUED

CHEMICALS	CPVC	PP	PTFE	PVC	PIG/GF/Fibertec™	PVDF	Ultem® (GF 40%)	EPDM	FPM	Nitrile (Buna N)	Hastelloy® C	Monel®	18-8 SS	316 SS	416 SS	titanium	CHEMICALS	CPVC	PP	PTFE	PVC	PIG/GF/Fibertec™	PVDF	Ultem® (GF 40%)	EPDM	FPM	Nitrile (Buna N)	Hastelloy® C	Monel®	18-8 SS	316 SS	416 SS	titanium
Ammonium Bichrom.	A	A	A	A	A	A	A	A	A								Aqua Regia	X	X	A	X	A		C	C	C	X	X	X	X	X	A	
Ammonium Bifluoride	A	A	A	A	A	A	A	A	B	A	B	X	X	X		Argon	X		A	X			A	A	C		A	A	A	A	A		
Ammonium Bisulfide					A	A	A										Arochlor							A	X	A	A	B	A				
Ammonium Carbonate	A	A	A	A	A	A	A	A	C	AB	AB	AB	AB	B	A		Aromatic Hydrocarbons	X			X	X		X	A	X						A	
Ammonium Casenite														A			Arsenic Acid	A	A	A	A	A	A	A	A	B	AB	A	AB	B	AB		
Ammonium Chloride	A	A	A	A	A	A	A	A	A	B	AB	A	X	AB	X	A	Arsenous Acid																
Ammonium Dichromate	A	A	A	A	A	A	A	A	A								Aryl Sulfonic Acid	X	X		X	X											
Ammonium Fluoride 20%	A	A	A	A	C	A	A	A									Asphalt	X	A	A	X	X	A	X	A	B	A	A	A	A	AB	A	
Ammonium Fluoride	A		A	A					B	A			X			BC	Aviation Fuel				A												
Ammonium Hydroxide	X	A	A	A	A	A	X	A	B	B	A	X	AC	A	A	A	Aviation Turbine Fuel				A												
Ammonium Nitrate	B	A		B	A	A		A	A	AB	C	A	A	B	A		Baking Soda				A				A	A	A						A
Ammonium Oxalate											A	A	A	A	A		Barium Carbonate	A	A	A	A	A	A	A	A	A	B	AB	AB	B	AB	A	
Ammonium Persulfate	A	C	A	A	A	A	B	C	C	B	X	AC	A	AC	A		Barium Chloride	A	A	A	A	A	A	A	A	A	A	AB	A	AB	BC	A	
Ammonium Ph. Di Basic	A	A	A	A	A	A		A	A	A	AB	AB	BC	A	AC	A	Barium Cyanide															A	
Ammonium Ph. Mono	A	A	A	A	A			A	A	A	A	B	C	A	A	A	Barium Hydrate			A					A	A	A	A	A	A	A	A	
Ammonium Ph. Tri.	A	A	A	A	A			A	A	A	A	AB	AB	A	AB	A	Barium Hydroxide	A	A	A	A	A	A	A	A	A	B	A	AB	AB	A		
Ammonium Phosphate	A	A	A	A	A	A	A	A	A	A					A		Barium Nitrate	A	A	A	A	A			A	A	X	AB	B	B	A		
Ammonium Salts	A	A	A	A	A	A		A	C	A			X				Barium Salts	A	A	A	A	A	A	A	A	A						A	
Ammonium Sulfate	A	A	A	A	A	A	A	C	B	A	AB	AB	A	B	A		Barium Sulfate	A	A	A	A	A	A		A	A	A	AB	AB	AB	C	AB	
Ammonium Sulfide	A	A	A	A	A	A	A	C	A	A		BC	A	C			Barium Sulfide	A	A	A	A	A	A		A	A	A	A	AB	A	B	A	
Ammonium Thiocyanate	A	A	A	A	A			A	A	A	A				A		Beer	A	A	A	A	A	A		A	A	C	A	A	A	A	A	
Ammonium Thiosulfate		A						A	A	A			AB	A	C	A		Beet Sugar Liquid	A	A	A	A	A			A	A	A					A
Ammonium, Fluoride 10%	A	A	A	A	C	A	A	A									Beet Sugar Liquor	A	A	A	A	A	A		A	A	A	A	A	A	B	A	
Ammonium, Fluoride 25%	A	A		X	X	A											Benzaldehyde	X	C		X	X	C		C	C	X	A	B	A	A	C	A
Amyl Acetate	X	X	A	X	X	C	A	X	C	A	A	AB	A	AB	A		Benzalkonium Chl.				A												
Amyl Alcohol	B	A	A	C	C	A	A	A	A	A	A	AB	A	A	AB		Benzene Sulf Ac.	X	X	A	X	X	B		X	A	C	B	B	A	AB	AB	
Amyl Borate			A		A		X	A	A								Benzene Sulf. Ac. 10%	X	X	A	X	X	B			A							
Amyl Bromide		A					X	B	X								Benzene	X	C	A	X	X	B	C	X	B	C	AB	A	A	AB	A	
Amyl Chloride	X	X	A	X	X	A	X	A	X	A	A	AB	A	AC	X		Benzoic Acid	A	A	A	A	A	A		B	A	X		B	B	A		
Aniline Chlorohydrate				X	X												Benzyl Alcohol	X	A	A	X	X	A	X	C	A	X		A	C	AB	A	
Aniline Hydrochloride	X	A	A	X	X	A	B	B	C						X		Benzyl Benzoate			A				C	A	X		C	AB	C			
Aniline	X	A	A	X	X	C	B	B	X	A	B	AB	A	B	AC		Benzyl Chloride	X	A	A					X	A	X	B		C	AB	C	
Anthraquinone Sulf. Ac.	A	A		A	A	A		A									Bismuth Carbonate	A	A	A	A	A	A		A	A	A						
Antichlor			A				A	A	A								Black Liquor	A	A	A	A	A	A		B	A	A	AC		A	A	AC	
Anti-Freeze	A	A	A	A	C	A	A	A	A				A				Borax	A	A	A	A	A	A		A	A	A	A	A	A	A	A	
Antimony Chloride	A	A			A		A	X									Boric Acid	A	A	A	A	A	A		A	A	B	A	AC	B	B	BC	A
Antimony Pentachloride		A						X									Brake Fluid		A			C	A	X	C	A	A	A	A	A	A	A	
Antimony Trichloride	A	A	A	A	A	A	A	A	A	AB	X	A	X	AB			Brewery Slop							A	A							A	
																	Brine Acid	A	A	A	A	A	A		A	A	A						

A = Excellent, no effect • B = Good, minor effect • C = Fair, data not conclusive, testing recommended • X = Not recommended.

Ratings are based on testing at an ambient temperature of 70°F. The chemical resistance table is for reference only. End users should test to determine application suitability. Butterfly valves, Solenoid valves, Diaphragm valves and all other valves with elastomers fully exposed to process media should derate elastomer scores by one level (i.e. "B" becomes "C", "C" becomes "X").



# HAYWARD®

## Chemical Resistance Guide, CONTINUED

CHEMICALS	CPVC	PP	PTFE	PVC	PVC-GF/Fibertec™	PVDF	Ultam® (GF 40%)	EPDM	FPM	Nitrile (Buna N)	Hastelloy® C	Monel®	18-8 SS	316 SS	416 SS	Titanium	CHEMICALS	CPVC	PP	PTFE	PVC	PVC-GF/Fibertec™	PVDF	Ultam® (GF 40%)	EPDM	FPM	Nitrile (Buna N)	Hastelloy® C	Monel®	18-8 SS	316 SS	416 SS	Titanium
Brine Acid	A	A	A	A	A	A	A	A	A	A							Butyric Acid	B	A	A	X	A	B	B	B	X	A	AC	AB	X	A		
Brine	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A		Cadmium Cyanide	A			A												
Bromic Acid	A	X	A	A	A	A	B	A	A	A			X				Cadmium Salts	A	A			A											
Bromine Gas		X	A	C	C	A	X	A	X	X	X	X	X	A			Caffeine Citrate		A	A	A												
Bromine Dry			A				X	A	X	A	A	X	X	X	AB		Calamine		A														
Bromine Liquid, Br	X	X	A	X	X	A	X	A	X	A	A	X	X	X	X		Calcium Acetate	A	A	A	A	A	A	A	X	B	AB	C	AB	C			
Bromine Water	C	C	A	X	X	A	X	A	C	A	X	X	X	X	X	A	Calcium Bisulfate	A	A	A	A	A	A	X	A	A		C	X	X			
Bromobenzene	X		A	X	X		X	A	C								Calcium Bisulfide	A	A	A	A	A	A	X	A	A	A		AB	A		A	
Bromotoluene	X	X	X	X													Calcium Carbonate	A	A	A	A	A	A	A	A	A	B	AB	A	AB	A	AB	
Butadiene Gas	A	A	A	B	C	A	X	A	X	AC	A	A	A	A			Calcium Chlorate	A	A	A	A	A	A	A	A	A	AB	AC	A	B	C	A	
Butane	A	A	A	A	A	A	X	A	A	A	A	A	A	A	A		Calcium Chloride	A	A	A	A	A	A	A	A	A	A	AC	X	B	X	A	
Butanediol	B		A	A	A		X	A									Calcium Cyanide		A														
Butter			A							A	A						Calcium Hydroxide	A	A	A	A	A	A	A	A	A	A	A	AB	AB	A	A	
Buttermilk				A						A	A						Calcium Hypochloride		A														
Butyl Acetate	X	C	A	X	X	B	C	B	X	C	A	A	A	A	A		Calcium Hypochlorite	A	B	A	A	A	A	A	A	A	B	A	X	X	AB	X	
Butyl Acrylate Pure	X	X	A	X	X	A			A	X							Calcium Nitrate	A	A	A	A	A	A	A	A	B	A	AB	A	AB	A	AB	
Butyl Acrylate Satur.									A	X							Calcium Oxide	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	
Butyl Alcohol (Butanol)	A	A	A	C	C	A			A	A	A	A	A	A	A		Calcium Phosphate		A														
Butyl Amine	X	X	A	X	X	B			X	X	C	AB					Calcium Sulfate	A	A	A	A	A	A	A	A	A	AB	A		A	AB	A	
Butyl Benzoate			A						A	A	X						Calcium Sulfide	A	A	A	A	A	A	A	A	A	AB	A	AB	BC			
Butyl Bromide			A			A			B	X							Calcium Thiosulfate		A														
Butyl Butyrate			A						B	C	X						Calgon		C	A		A											
Butyl Carbitol	X		A						A	A	C						Cane Sugar Liquors	A	A	A	A	A	A	A	A	A		A	A	A	B		
Butyl Cellosolve	X		A	A	A	A			B	X	C	A	A	C	A	AC	Caprylic Acid		A			A										C	
Butyl Chloride			A			A			A	X	A	A	A	A	A		Carbinol		A														
Butyl Diol	A	A	A	B	C	A			A	A							Carboxlic Acid	A	A														
Butyl Ether	X	X	A	X	X	A			X	X	B			A	A	A	Carbon Bisulfide	X	X	A	X	X	A		A	X			C				
Butyl Formate			A									X					Carbon Dioxide	A	A	A	A	A	A	B	A	A	A	A	A	A	A	A	
Butyl Hydrate			A						B	A	A						Carbon Disulfide	X	X	A	X	X	A	X	A	C	A	B	A	A	AC	AB	
Butyl Hydride			A						X	A	A						Carbon Monoxide	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	
Butyl Hydroxide			A						B	A	A						Carbon Tetrachloride	X	X	A	X	X	A	A	X	B	C	A	A	AB	AB	A	
Butyl Mercaptan			A	X	X	A											Carbonic Acid	A	A	A	A	A	A	A	A	B	A	AB	A	AC	AB		
Butyl Phenol	A	A		C	C	A					A			A	A		Casein		A			A											
Butyl Phthalate	X	A	A	X	X	A			B	C	X	AB	AB	AB	AB	A	Castor Oil	C	A	A	A	A	A	B	A	A	A	A	A	A	A	A	
Butyl Stearate			A			A			B	A	B			C	A	AC	Catsup	A	A	A	A	A	A		A	A	A		A	A			
Butylbenzene			A						A	X							Caustic Lime																(See Calcium Hydroxide)
Butylene	A	X	A	A	A	A			X	A	B	A	A	A	A		Caustic Potash																(See Potassium Hydroxide)
Butyraldehyde			A						B	X	X	A					Caustic Soda																(See Sodium Hydroxide)

A = Excellent, no effect • B = Good, minor effect • C = Fair, data not conclusive, testing recommended • X = Not recommended.

Ratings are based on testing at an ambient temperature of 70°F. The chemical resistance table is for reference only. End users should test to determine application suitability.

Butterfly valves, Solenoid valves, Diaphragm valves and all other valves with elastomers fully exposed to process media should derate elastomer scores by one level (i.e. "B" becomes "C", "C" becomes "X").

# Chemical Resistance Guide, CONTINUED

CHEMICALS	CPVC	PP	PTFE	PIG	PICGF (Fibertec®)	PVDF	UHMW® (GF 40%)	EPDM	FPM	Nitrile (Buna N)	Hastelloy® C	Monel®	18-8 SS	316 SS	416 SS	Titanium	CHEMICALS	CPVC	PP	PTFE	PIG	PICGF (Fibertec®)	PVDF	UHMW® (GF 40%)	EPDM	FPM	Nitrile (Buna N)	Hastelloy® C	Monel®	18-8 SS	316 SS	416 SS	Titanium	
Cellosolve	X	A	A	B	A	C	B	C	C	A	A	C	C	AC	AB		Copper Fluoride	A	A	A	A	A	A	A	A	A	C	A						
Chloral Hydrate	A	A	A	A	A			A	C								Copper Nitrate	A	A	A	A	A	A		A	A	A	X	AB	A	B	A		
Chloric Acid 20%	A	X	A	A	A												Copper Salts	A	A	A	A	A	A		A	A	A							
Chloric Acid	A	A	A	A	A			X	AB	X	X	X	X	X		Copper Sulfate 5%	A	A	A	A	A	A			A	A			A	B	A			
Chlorinated Glue							B	A	C							Copper Sulfate	A	A	A	A	A	A		A	B	B	A	AB	AB	A	AB	A		
Chlorine Dioxide	A	C	A	A	A	A	X	A		A	X	X	X	X	AB	Corn Oil	A	A	A	A	A	A		B	A	A	A	A	A	A	A			
Chlorine Gas, Dry	X	X	A	X	X	A	X	B	C	A	AB	B	B	BC	X	Corn Syrup	A	A	A	A	A	A		B	A	A		A						
Chlorine Gas, Wet	X	X	A	X	X	A	C	X	C	A	C	X	X	X	A	Cottonseed Oil	A	A	A	A	A	A		B	A	B	A	A	AB	A	A			
Chlorine Water	A	C	A	A	A	A	B	A	C	A	C	X	X	X	A	Cream	A	A							A	A		A						
Chlorine, Dry	X	A					B	C	X							Creosol	X	C	A	X	X	C		X	A	X		A	A					
Chlorine, Liquid	X	X	C	X	X	A			C							Creosote	X	A	X	X				X	A	B	A	A	A	AB	A			
Chloroacetic Acid		X	A	A			B	X	X	A	B	X	X	X	A	Cresols	X	C	A	X	X	A		X	A	X	AB		A	A	AB			
Chlorhydr. Alum		A														Cresylic Acid	C	A	A	C	A	A		X	A	X	A	A	A	A	A			
Chlorosulfonic Acid	X	X	A	X	X	C	X	X	X	A	AC	X	X	X	A	Croton Aldehyde	X	A	A	X	X	C		B	A									
Chocolate Syrup	A									A	AB	AB	A	A	A		Crude Oil	A	A	A	A	A	A		X	A	X	A	AB	A	A	A		
Chresylic Acid 50%			A	B		B			A	X						Cryolite	B	A	A	B	A	A		A	A	B								
Chrome Alum	A	A	A	A	A				A	A						Cupric Fluoride	A	A	A	A	A	A		A	A									
Chrome Alum	A	A	A	A	A	A			A	A						Cupric Nitrate			A						A	A	A							
Chromic Acid 10%	A	B	A	A	A	A	A	B	A	X						Cupric Salts	A	A	A	A	A	A		A	A				X					
Chromic Acid 20%	A	X	A	B	C	A	B	B	C							Cupric Sulfate	A	A	A	A	A	A		A	A	A								
Chromic Acid 30%	A	X	A	B	C	A			A	X						Cutting Oil			A					X	A	A		A	A	A				
Chromic Acid 5%	A	X	A	A	A	A	A	A	A	X						Cyanic Acid			A						A	A	B	A						
Chromic Acid 50%	X	X	A	X	X	A	C	B	A	X				X		Cyclohexane	X	X	A	X	X	A		X	A	C	AB	A	AC	A	AC	A		
Chromium Alum	A	A	A	A	A	A	A	A	A							Cyclohexanol	X	A	A	X	X	C		B	A	B	A	C	A	AC				
Citric Acid	A	A	A	A	A	A	A	A	B	A	AB	AB	B	BC	A	Cyclohexanone	X	B	A	X	X	C		C	X	C	A	BC	C	A	BC			
Citric Oils	X	A	A				B	A	A	A						Decalin	X	A	A	X	X	A		X	A	X								
Cobalt Chloride		A							A	A	A					Decanal			A					X	X									
Coconut Oil	A	A	A	A	A	A	B	A	A	A	BC		A	AC		Decane			A			A		X	A	B								
Cod Liver Oil		A						A	A	B	A	A	A	A	A	Detergents	B	B	A	A	A	A		A	A	AB	A		A	A	A			
Coffee	A	A						A	A	A	A	AC	A	A	A	Detergents, Heavy Duty	A	A		A	A	A												
Coke Oven Gas	A	A	A	X	X	A	A	A	X						Developers			A						A	A	AB	A	A	A	A	A			
Cola Concentrates	A															Dextrin	A	A	A	A	A	A		A	A			A	A					
Copper Acetate	A	A	A	A	A	A		A	X	B	A	X	A	A	AB	Dextrose	A	A	A	A	A	A		A	A	A	A	A	A	A	A	A		
Copper Borofluoride	A	A	A	A	A	A		A	A							Diacetone Alcohol	X	C	A	X	X	B		A	X	C	A	A	A	A	A	A	A	
Copper Carbonate	A	A	A	A	A	A		A	A	X	A	X	A	A	BC	Diallyl Phthalate																		
Copper Chloride	A	A	A	A	A	A		A	A	A	A	X	X	X	BC	Diazo Salts	A	A		A	A	A												
Copper Cyanide	A	A	A	A	A	A		A	A	B	A	X	A	B	AB	Dibenzyl Ether			A			C												
Copper Fluoborate		A	A	A				A	B	B	C	X	X			Dibutyl Amine	A		A		X	C	C											

A = Excellent, no effect • B = Good, minor effect • C = Fair, data not conclusive, testing recommended • X = Not recommended.

Ratings are based on testing at an ambient temperature of 70°F. The chemical resistance table is for reference only. End users should test to determine application suitability.

Butterfly valves, Solenoid valves, Diaphragm valves and all other valves with elastomers fully exposed to process media should derate elastomer scores by one level (i.e. "B" becomes "C", "C" becomes "X").



## Chemical Resistance Guide, CONTINUED

CHEMICALS	CPVC	PP	PTFE	PVC	PVC-GF (Fiberglass)	PVDF	UHMW® (GF 40%)	EPDM	FPM	Nitrile (Buna N)	Hastelloy® C	Monel®	18-8 SS	316 SS	416 SS	Titanium
Dibutyl Ether		A		A		C	C	C		A	A	A				
Dibutyl Phthalate	X	B	A	X	X	A	A	B	X	AB			AB	A		
Dibutyl Sebacate		A	B	A		B	C									
Dichlorobenzene	X	A	X	X	A	X	X	B	X	A		A	A	A		
Dichloroethane		A	X	X		X		C		A	A	A	A	AB		
Dichloroethylene	X	X	A	X	X	A		X	AB	A		BC				
Dichloroisopropyl Ether					A											
Dichloromethane			A			X	X	B	X							
Diethyl Phthalate										A	AB	A				
Diesel Fuel	A	B	A	A	A	A	X	A	A	A	A	A	A	A		
Diethanolamine										A	A	A	A	A		
Diethyl Cellosolve					A		X									
Diethyl Ether	X	B	A	X	X	A		C	C	X	A	B	AB	A	AB	A
Diethyl Ketone			A				B	X	X							
Diethyl Oxide			A				X	X	B							
Diethylamine	X	A	A	X	X	C		B	X	B		BC	A	A	A	X
Diethylbenzene			A					X	A	X						
Diethylene Glycol	A	A	A			A		A	A	B	AB	A	A	A	A	A
Diethylenetriamine			A		A			B								
Diglycolic Acid	A	A	A	A	A	A	A	A								
Diisobutyl Ketone					A		X	X								
Diisobutylene			A		A		X	A				A				
Diisooctyl Phthalate			A			A	B	B								
Diisopropyl Ketone			A		B		B	X		C	A	A	A			
Dimethyl Amine	X	A	A	X	X	B		C	X	B						
Dimethyl Benzene			A				X	A	X							
Dimethyl Ether			A				B	B	B	C	C	C	C	A		
Dimethyl Formamide	X	A	A	X	X	A	X	B	C	B	A	A	A			
Dimethyl Ketone			A					A	X	X						
Dimethyl Phthalate			A		B		B	B	X	A			A			
Dimethylamine	X	A		X	X	X		X	X							
Dioctyl Phthalate	X	X	A	X	X	A		B	A	X	A		A	A	A	A
Dioxane	X	B	A	X	X	X	X	B	X	X	X	A	A	AB		
Dioxolane						X	X	X								
Diphenyl Ether									A			A				
Diphenyl Oxide							X	A	X							
Diphenyl			A				X	A	X	B	AB	B	B	A	A	
Dipropylene Glycol			A				A	A								
CHEMICALS	CPVC	PP	PTFE	PVC	PVC-GF (Fiberglass)	PVDF	UHMW® (GF 40%)	EPDM	FPM	Nitrile (Buna N)	Hastelloy® C	Monel®	18-8 SS	316 SS	416 SS	Titanium
Disodium Phosphate	A	A	A	A	A	A	A									
Distilled Water	A	A		A	A	A										
Divinylbenzene	X	X			X	X	X									
Dolomite								A					B	A	A	
Dowtherm														A	A	A
Dry Cleaning Solvents								A		X			X	A	A	
Epichlorohydrin	X	A	A	X						A			X	X	A	A
Epsom Salt	A	A	A	A	A	A				A	A	A	A	A	AB	A
Esters	X	C	A	X	X	A										
Ethane								A					X	A	A	A
Ethanol	B	A	A	A	A	A	A			A	B	A			A	B
Ethanolamine	X	X	A	X	X	X				A	X	B	AB	A	A	A
Ether Alcohol								A					A	B	C	
Ethers	X	C	A	X	X					C	C	X	A	A	A	A
Ethyl Acetate	X	C	A	X	X	A	C			B	X	X	A	A	A	BC
Ethyl Acetoacetate	X	A	X	X	A					A	X	X				
Ethyl Acrylate	X	X	A	X	X	A	C			B	X	X	A	A	A	A
Ethyl Alcohol	A	A	A	A	A	A	A			A	B	A	A	A	A	A
Ethyl Benzene	X	A					A			X	A	X	A	A	A	A
Ethyl Bromide	X												A	A	A	
Ethyl Chloride	X	X	A	X	X	A				A	A	B	B	AB	A	A
Ethyl Ether	X	B	A	X	X	A				X	C	X	A	B	AB	AB
Ethyl Formate							A				B	B	X		A	A
Ethyl Hexanol							A			A	A	B				
Ethyl Sulfate							A				X	C	A	A	C	X
Ethylene Bromide	X	C	A	X	X	A				C	B	X	AB		AB	B
Ethylene Chloride	X	C	A	X	X	A				C	A	X	A	AB	A	A
Ethylene Chlorohydrin	X	A	A	X	X	A				A	A	X	B		AB	BC
Ethylene Diamine	X	A	A	X	X	C	X	A	X	A	AC		A	A	A	A
Ethylene Dichloride	X	C	A	X	X	A				X	A	X	A	AB	A	A
Ethylene Glycol	C	A	A	A	A	A	A			A	A	A	A	A	A	A
Ethylene Oxide	X	X	A	X	X	A				X	X	X	A	A	AB	A
Extrin	A	A	A	A		A				A	A					
Fatty Acids	B	A	A	A	A	A				X	A	B	A	A	A	B
Ferric Acetate							A	B	B				X	X		
Ferric Chl. Anhydrous	A	A	A	A	A	A				A	A	B				X
Ferric Hydroxide	A	A	A	A	A	A				A	C					
Ferric Nitrate	A	A	A	A	A	A				A	A	A	AB	X	A	B

A = Excellent, no effect • B = Good, minor effect • C = Fair, data not conclusive, testing recommended • X = Not recommended.

Ratings are based on testing at an ambient temperature of 70°F. The chemical resistance table is for reference only. End users should test to determine application suitability.  
Butterfly valves, Solenoid valves, Diaphragm valves and all other valves with elastomers fully exposed to process media should derate elastomer scores by one level (i.e. "B" becomes "C", "C" becomes "X").

# Chemical Resistance Guide, CONTINUED

CHEMICALS	CPVC	PP	PTFE	PVC	PVC GF	PVDF	Ultram® (GF 40%)	EPDM	FPM	Nitrile (Buna N)	Hastelloy® C	18-8 SS	316 SS	416 SS	Titanium	CHEMICALS	CPVC	PP	PTFE	PVC	PVC GF	PVDF	Ultram® (GF 40%)	EPDM	FPM	Nitrile (Buna N)	Hastelloy® C	18-8 SS	316 SS	416 SS	Titanium
Ferric Sulfate	A	A	A	A	A	A	A	A	B	A	B	A	B	B	A	Glycerol	A	A	A	A	A	A	A	A	A	A	A	A	A	A	
Ferrous Chloride	A	A	A	A	A	A	A	A	B	AB	X	X	X	X	A	Glycolic Acid	A	A	A	A	A	A	A	A	A	A	A	A	A	A	
Ferrous Nitrate	A	A	A	A	A	A	B	A	A							Glycols	A	A	A	A	A	A	A	A	A	AB					
Ferrous Sulfate	A	A	A	A	A	A	A	A	A	AB	A	C	B	A		Glyoxal															
Fish Solubles	A	B		A	A											Gold Monocyanide															
Fluoboric Acid	A	A		A	A	A	B	A	A	B	A	A	B	X		Grape Juice	A			A	A										
Fluorine Gas (Wet)	A	B	A	A	C	A	A	A	X	A	A					Grape Sugar	A	A	A	A	A	A	A	A	A	A					
Fluorine Liquid	X	B	C	X	A		C	B	X			X		X		Grease	A	A	A	A	A	A	X	A	B	A	A	A	A	A	
Fluosilicic Acid 25%	A	A	A	A	A	A	A	A	A	B	A	X	B	C	X	Green Liquor	A	A	A	A	A	A	A	A	B	A					
Formaldehyde 35%	A	A	A	A	A	A	A	A	A				B			Helium	A														
Formaldehyde 50%	A	A	A	A	A	A	X	B								Heptane	A	B	A	A	A	A	X	A	A	A	A	A	A	A	
Formaldehyde	A	A	A	X	B	A	A	B	B	B	A	A	A	B	A	Hexane	A	B	A	X	X	A	A	X	A	A	A	A	A	A	
Formic Acid	A	A	A	A	A	A	B	A	X	C	A	AB	B	B	B	Hexene	A														
Freon 11	A	A	A	X	X	A	X	B	B	A	A	A	A	A		Hexyl Alcohol	A	A	A	A	A	A	B	A	A	A	A	A	A	A	
Freon 113	B	X	A	B	C	A	X	B	A	A	A	A	A	A		Honey	A	A	A	A	A	A	A	A	A	A					
Freon 114		A	A	A	A	C	A	A				A				Hydraulic Oil (Synth.)	X		C				A	C	A	A	A	A			
Freon 12 (Wet)		A	A	B	C		B	A	A							Hydraulic Oil			A		X	A	A	A	A	A					
Freon 12	A	A	A	C	C	A	A	B	B	A	AB	A	A	A		Hydrazine	X	X	A	X	X	X	A	X	C		A	A			
Freon 22	X	A	A	X	X	A	B	X	X			A	A	A		Hydrobromic Acid 20%	A	A	A	A	A	A	A	A	X			X	X	A	
Freon TF																Hydrobromic Acid 50%	A	B	A	A	A	A	A	A	X			X	C	X	
(See Freon 113)																															
Fructose	A	A	A	A	A	A	A	A	A	A	A	A	A	A		Hydrobromic Acid	A	B	A	A	A	A	A	A	X	A					
Fruit Juice	A	A	A	A	A	A		A	A	A	A	A	A	A		Hydrochloric Acid 10%	A	A	A	A	A	A	A	A	B			X	X	C	
Fruit Pulp	A	A		A	A	A		A								Hydrochloric Acid 20%	A	A	A	A	A	A	A	A	B			X	X	C	
Fuel Oil		B	A	B	C	A	X	A	A	A	A	A	A	A		Hydrochloric Acid 25%	A	A	A	A	A	A	A	A	C			X	X		
Fumaric Acid		A						A	A			A				Hydrochloric Acid 37%	A	A	A	A	A	A	C	A	C			X	X	C	
Furan		A					X	X	B							Hydrochloric Acid	A	A	A		A	A	B	X	X	A					
Furfural (Ant Oil)	X	C	A	X	X	B	B	X	X	AB	B	AB	A	A		Hydrocyanic Acid 10%	A	A	A	A	A	A	A	A	B			X	X		
Furfuryl Alcohol			A		B		C	X			A					Hydrocyanic Acid	A	A	A	A	A	A	A	A	B	A	A	B	A		
Gallic Acid	A	A	A	A	A	A	A	A	A	B	B	A	A	B		Hydrofluoric Acid 10%	A	A	A	A	C	A	A	B				X	X		
Gas, Natural	A	A		A	A	A	X	A	A	A	A					Hydrofluoric Acid 20%	A	A	A	A	C		A	A	X			X	X	X	
Gasoline, Leaded	X	X	A	A	A	A	X	B	A	A	A	A	A	A		Hydrofluoric Acid 30%	A	A	A	A	C	A	A	A				X	X		
Gasoline, Sour	B	X	A	A	A	A	X	A	A	A	X	A	A	A		Hydrofluoric Acid 40%	C	A	A	B	C	A	A	A				X	X		
Gasoline, Unleaded	X	X	A	C	C	A	X	B	A	A	A	A	A	A		Hydrofluoric Acid 50%	C	A	A	X	X	B	A	A	C			X	X	X	
Gelatin	A	A	A	A	A	A	A	A	A	A	A	A	A	A		Hydrofluoric Acid 65%	C	A					B	A	X			X	X		
Gin	A	A	A	A	A	A	A	A	A							Hydrofluoric Acid 75%	C	A	A	X	X	A	X	A	X	A	X	X	X		
Glucose	A	A	A	A	A	A	A	A	A	A	A	A	A	A		Hydrofluosilic Acid	A	A	A	A	A	A	A	A	B	A	X	X	X	A	
Glue	A	A	A	A	A	A	B	A	A	A	A	A	A	A		Hydrofluosilicic Acid 20%	A	A	A	A	A	A	A	A	B			X	X	X	
Glycerine	A	A	A	A	A	A	A	A	A	A	A	A	A	A		Hydrogen Chl. Gas Dry	A			A								A	A	X	

A = Excellent, no effect • B = Good, minor effect • C = Fair, data not conclusive, testing recommended • X = Not recommended.

Ratings are based on testing at an ambient temperature of 70°F. The chemical resistance table is for reference only. End users should test to determine application suitability.

Butterfly valves, Solenoid valves, Diaphragm valves and all other valves with elastomers fully exposed to process media should derate elastomer scores by one level (i.e. "B" becomes "C", "C" becomes "X").



# HAYWARD®

## Chemical Resistance Guide, CONTINUED

CHEMICALS	CPVC	PP	PTFE	PVC	PVC-GF/Fiberloc™	PVDF	Ultem® (GF 40%)	EPDM	FPM	Nitrile (Buna N)	Hastelloy® C	18-8 SS	316 SS	416 SS	Titanium	CHEMICALS	CPVC	PP	PTFE	PVC	PVC-GF/Fiberloc™	PVDF	Ultem® (GF 40%)	EPDM	FPM	Nitrile (Buna N)	Hastelloy® C	18-8 SS	316 SS	416 SS	Titanium		
Hydrogen Cyanide	A	A	A	A	A	A	A	A	B	A	B	A	C			Latex	A	A								B	A	B	A	A	A		
Hydrogen Fluoride	X	A	X	X	A					B	AB	AB	C				Lauric Acid	A	A	A	A	A	A										
Hydrogen Peroxide 10%	A	A	A	A	A	A		A				C	B	C			Lauryl Chloride	A	A	A	A	A	A										
Hydrogen Peroxide 30%	A	C	A	A	A	A	A	B	A	X		B	B	B			Lead Acetate	A	A	A	A	A	A	A	C	B	AB	A	B	B	B	A	
Hydrogen Peroxide 5%	A	A	A	A	A	A	A	A	A			B					Lead Chloride	A	A	A	A	A	A	A	A	A							
Hydrogen Peroxide 50%	A	A	A	B	C	A	C	A	X			C					Lead Nitrate	A	A	A	A	A	A	A	A	A	B	B	C	B			
Hydrogen Peroxide 90%	X	X	A	X	C	A	C	B	X				X					Lead Sulfate	A	A	A	A	A	A	A	A	A						
Hydrogen Peroxide		A	A	A	A	A	B	A	C	A	AB	AB	B	B	B			Lemon Oil	A	X	X	A	A	A					A				
Hydrogen Phosphide	A	A	X	C	A			C										Ligroin	X	C	X	X	A	C	A	A	A	A	A	A	A		
Hydrogen Sulf. (Aq. Sol.)	A	A	A	A	A		A	C	C			A	C	A				Lime - Sulfur Solution	A	A		A	A	A		X				B			
Hydrogen Sulfide (Dry)	A	A	A	A	A	A	A	A	A	A	B	C	A	C				Lime															(See Calcium Oxide)
Hydrogen Sulfide	A	A	A	A	A	A	A	A	A	A	BC	AB	C																				
Hydrogen	A	A	A	A	A	A	A	A	A	A	A	A	A	A																			
Hydroquinone	A	A	A	A	A	A	A	A	X	B	A	C																					
Hydroxide Alum	A	A	A	C	A	A	A	C	A				A	A	A																		
Hydroxyacetic Acid 70%	A		A	A		A	A	A	A			B																					
Hydroxyacetic Acid	A							A	A						A																		
Hydroxylamine Sulfate	A	A	A	A	A	A	A																										
Hypochlorous Acid	A	A	A	A	A	A	B	B	X	A	X	X																					
Ink	A				A				A	A	AC	A	A																				
Iodine Solution	A	C	A	X	X	A	A	A	A	C	A	A	B	X	X	A																	
Isobutyl Alcohol		A			A	A	A	A	B	A	A	A	A		A																		
Isooctane	A	A	A	A	A	A	X	A	A	A	A	A																					
Isophorone	X		X	X			X	X		A																							
Isopropyl Acetate	A						B	X	X	B	AB		B																				
Isopropyl Alcohol	A	A	A	A	A	B	A	A	B	A	AB	AB	A	A																			
Isopropyl Ether	X	C	A	X	X	A	X	X	B	A	A	A	A																				
Jet Fuel JP-3	A	A					X	A	A	A	A	A	A	A																			
Jet Fuel JP-4	A	C	A	A	A	A	X	A	B	A	A	A	A	A																			
Jet Fuel JP-5	A	C	A	A	A	A	A	X	A	A	A	A	A	A																			
Kerosene	A	A	A	A	A	A	X	A	A	A	A	A	A	A	A																		
Ketones	X	A	A	X	X	A	C	X	X	A	A	A	A	A	A	A																	
Kraft Liquor	A	A		A	A	A																											
Lacquer Thinner	B	A	C	C			A	X	A	A	A	A	A	A	A	A																	
Lacquer	A	A					X	X	X	A	A	A	A	A	A	A																	
Lactic Acid	A	A	A	A	A	A	B	B	B	A	AB	A	A	C	B																		
Lard Oil	A	A	A	A	A	A	C	A																									
Lard	A	A	A	A	A	A	C	A	A	AC	A	A	A	A																			

A = Excellent, no effect • B = Good, minor effect • C = Fair, data not conclusive, testing recommended • X = Not recommended.

Ratings are based on testing at an ambient temperature of 70°F. The chemical resistance table is for reference only. End users should test to determine application suitability. Butterfly valves, Solenoid valves, Diaphragm valves and all other valves with elastomers fully exposed to process media should derate elastomer scores by one level (i.e. "B" becomes "C", "C" becomes "X").

# Chemical Resistance Guide, CONTINUED

CHEMICALS	CPVC	PP	PTFE	PVC	PIC GF	PVDF	Ultram® (GF 40%)	EPDM	FPM	Nitrile/Buna N	Hastelloy® C	18-8 SS	316 SS	416 SS	Titanium	CHEMICALS	CPVC	PP	PTFE	PVC	PIC GF	PVDF	Ultram® (GF 40%)	EPDM	FPM	Nitrile/Buna N	Hastelloy® C	18-8 SS	316 SS	416 SS	Titanium		
Mercuric Sulfate	A	A	A	A	A	A	A	A	A							Milk	A	A	A	A	A	B	A	A	A	A	BC	A	A	A			
Mercurous Nitrate	A	A	A	A	A	A	A	A	A	X	A					Mineral Oil	A	A	A	B	A	A	A	X	A	A	A	A	A	A			
Mercury	A	A	A	A	A	A	A	A	A	B	A	A	A	B		Molasses	A	A	A	A	A			C	A	A	A	A	A	A			
Methacrylic Ac.Glacial			X													Monochlorobenzene	B	A			A			X	A	A	AB						
Methane Sulfonic Ac.			A		A											Monochloroacetic Acid	A	B	A	A	A	A		C	B	A	B		X				
Methane	A	A	A	A	A	A	C	A	A	A	A	A	A	A		Monoethanolamine	X	A	X	X	X			A	A	A	AB	A	A	A			
Methanol (Methyl Alcohol)	X	A	A	A	A	A	A	A	X	A	A	A	AB	A	A	Morpholine	A							A				A					
Methoxyethyl Oleate			A	A												Motor Oil	A	C	A	A	A	A	A	X	A	A	A	A					
Methyl Cellosolve	X	A		X	X	A	B	X	X	A	A	AC				Mustard	A	A		A	A			A	B	A	BC	A	A				
Methyl Acetate	X	B	A	X	X	A	B	X	X	AB	A	A				Naphtha	A	A	A	A	A	A		X	A	B	A	A	A	A			
Methyl Acetone		A						X	X	AB	A	A				Naphthalene	X	B	A	X	X	A		X	B	X	A	B	B	A			
Methyl Acrylate		A		A			B	X	X	AB	A	A				Natural Gas	A	A		A	A	A		X	A	A	A	A	A				
Methyl Alcohol	X	A	A	A	A	A	A	X	A				A	A		Neon		A						A	A	A		A					
Methyl Benzene																Nickel Acetate	A	A	A	A	A	A		A	X	B	A	C					
(See Toluene)																																	
Methyl Bromide	X	X	A	X	X	A	C	A	X	AB		A				Nickel Chloride	A	A	A	A	A	A		A	A	B	A	AB	AC	B	X	A	
Methyl Butanol			A					B	A							Nickel Cyanide	A			A	A												
Methyl Butyl Ketone		A					B	X	X			A				Nickel Nitrate	A	A	A	A	A	A		B	A	A	B	B	A	B			
Methyl Chloride	X	X	A	X	X	A	C	C	C	A	A	A	A	B	A	Nickel Sulfate	A	A	A	A	A	A		A	A	A	AB	AB	A	C	B		
Methyl Chloroform	X	C	A	X	X	A	X	B		A	C					Nickel	A	A	A	A	A	A		A	A	A							
Methyl Ether		A					C	C	B	C	C	C				Nicotine Acid	A	A	A	A	A	A		A									
Methyl Ethyl Ketone	X	C	A	X	X	X	C	A	X	X	A	A	A	A	A	Nicotine	A	X	A	A	A	C											
Methyl Formate	X						A	X	AB		A					Nitrate Alum	A	A	A	A	A	A		A	B	A			A				
Methyl Isobutyl Alcohol									X							Nitric Acid 10%	A	A	A	A	A	A		B	A	X	B	X	A	B	A		
Methyl Isopropyl Ketone	X	B	A	X	X	A	C	X	X			A	A			Nitric Acid 20%	A	A	A	A	A			A	X	A	X	B	X	A	B		
Methyl Isobutyl Carbinol		A					A	A								Nitric Acid 30%	A	A	A	A	A	B	A	B	A	X	B	X	A	B			
Methyl Isobutyl Ketone	X	C	A	X	X	A	B	X	X			A	A			Nitric Acid 40%	A	C	A	A	B	A		X	A	X	B	X	A	C			
Methyl Methacrylate	X	A	A				C	X	X	X		C				Nitric Acid 50%	A	C	A	A	A	B		X	A	X	B	X	A	X			
Methyl Propanol		A					B	A	A							Nitric Acid 70%	A	X	A	X	X	X		A	X	C	X	B	X	A	X		
Methyl Salicylate	A	A		A	A	A										Nitric Acid Concentr.	A	X	A	X	X	X		X	C	X	B	X	A	C			
Methyl Sulfate	A	A		B	C	A										Nitric Acid Fuming	X	X		X	X	X							C				
Methylamine	X	X	A	X	X	C	A	B			A					Nitrobenzene	X	C	A	X	X	A	C	C	C	C	A	AB	B	B	B	A	
Methylene Bromide				X	X	X										Nitroethane		A		A	A	X											
Methylene Chloride	X	X	A	X	X	C	X	B	X	A	A	AC	A	B	A	Nitrogen Dioxide		A															
Methylene Iodine			A	X	X	C			A							Nitrogen		A															
Methylhexane		A					X	A	A							Nitroglycerine			X														
Methylisobutyl Carb.	A	A		A	A	A	A	A	A							Nitromethane			A		A	B											
Methylmethacrylate		A		A	A	A	X	X								Nitrous Oxide	A	A	A	A	A	A		A	A	A	X	C					
Methylsulfuric Acid	A	A	A	A	A	A										Ocenol	A	X	A	A	A	A											

A = Excellent, no effect • B = Good, minor effect • C = Fair, data not conclusive, testing recommended • X = Not recommended.

Ratings are based on testing at an ambient temperature of 70°F. The chemical resistance table is for reference only. End users should test to determine application suitability.  
Butterfly valves, Solenoid valves, Diaphragm valves and all other valves with elastomers fully exposed to process media should derate elastomer scores by one level (i.e. "B" becomes "C", "C" becomes "X").



# HAYWARD®

## Chemical Resistance Guide, CONTINUED

CHEMICALS	CPVC	PP	PTFE	PVC	PVC-GF/Fiberglass™	PVDF	Ultem® (GF 40%)	EPDM	FPM	Nitrile (Buna N)	Hastelloy® C	18-8 SS	316 SS	416 SS	Titanium	CHEMICALS	CPVC	PP	PTFE	PVC	PVC-GF/Fiberglass™	PVDF	Ultem® (GF 40%)	EPDM	FPM	Nitrile (Buna N)	Hastelloy® C	18-8 SS	316 SS	416 SS	Titanium
Octane	A			A	X	A										Peracetic Acid 40%	X	X	A	X	X	A	B	A							
Octyl Acid	A			A			C									Perchloric Acid 10%	A	A	A	A	A	A	B	A	X					B	
Octyl Alcohol						A	B	A		A	A		A			Perchloric Acid 70%	X	A	A	X	X	A	X	A	A	X				X	
Octylamine	A					X	C									Perchloroethylene	X	C	A	X	X	A	X	A	X	A	AB	A			
Oils, Crude Sour	X											C				Perphosphate	A	A	A	A	A	A	A	A							
Oils	X	A	A	A	A	A										Petrolatum	A	A	A	A	A	A	C	A	A	A	A	A	A		
Oils, Aniline	A	A	X	X		B	A	X			A	A				Petroleum (Sour)				A	A		X	A	A					C	
Oils, Anise											A					Petroleum Oils	A	B	A	A	A	A	X	A	A					A	
Oils, Bay							A				A					Phenols 100%	A	A	A	X	X	A	X	C	B	X	A	B	A	C	
Oils, Bone							A	A			A					Phenylacetate			A				B	X	X						
Oils, Castor		A			B	A	A				A					Phenylhydrazine Hydrochl	A	X		X	X	A									
Oils, Cinnamon	A					A					A					Phenylhydrazine	X	X	A	X	X	A	C	C	X						
Oils, Citric	A						A	A			A					Phosgene Gas	X	C		X	X	A	A	X	X						
Oils, Clove	B							A			A					Phosgene Liquid	X	X		X	X	C	A	X	X						
Oils, Coconut	A					A	A	A			A					Phosphate Alum			A				A	A	A						
Oils, Cod Liver	A					A	A	A			A					Phosphoric Acid 10%	A	A	A	A	A	A	A	A	C	A	A	A	B		
Oils, Corn	X	A			C	A	A				A					Phosphoric Acid 100%	A	A	A	A	A	A	B	A	X	A	A	B	B		
Oils, Cotton Seed	X	A	A	A	A	C	A	A			A					Phosphoric Acid 20%	A	A	A	A	A	A	A	A	C	A	A				
Oils, Creosote	X		X		X	A	B				A					Phosphoric Acid 40%	A	A	A	A	A	A	B	A	X	A	A	A	A		
Oils, Diesel Fuel	A		A		X	A	A				A					Phosphoric Acid 50%	A	A	A	A	A	A	A	A	C	A	A	B	B		
Oils, Fuel		A	A	A		X	A	B			A	A				Phosphoric Acid 80%	A	A	A	A	A	A	A	A	A	A	AB				
Oils, Linseed	X	A	A	A		X	A	A			A					Phosphoric Acid 85%	A	A	A	A	B	A	A	A	C	A	AB	B	C		
Oils, Mineral	A	A	A	A		X	A	A	A	A	A	A				Phosphoric Acid Crude			A				B	A	C		C	C			
Oils, Olive	X	A	A	A	A	B	A	A	A	A	A	A				Phosphorous Oxychloride			A							X					
Oils, Pine	X	A	A	A		X	A	C			A	A				Phosphorous Red	A	A	A	A	A	A									
Oils, Silicone	A		A				A	A				A					Phosphorous Trichloride	X	C	A	X	X	A	C	C	X	A	A	A	A	
Oils, Vegetable	X	A	A	A	A		A	A	A	A	A	A				Phosphorous Yellow	A	A	A	A	A	A									
Oleic Acid	B	A	A	A	A	A	A	C	B	B	A	A	A	B		Photographic Developer	A	A		A	A	A	A	A	A	A	C	A	A		
Oleum	X	X	A	X	X	X	X	X	X	X						Photographic Solutions	A	A	A	A	A	A	A	A	AB	AC	C				
Orange Extract	A	A			A												Phthalic Acid	X	X	A	X	X	A	A	A	X	C	B			
Oxalic Acid	A	A	A	A	A	A	A	A	B	A	B	A	B	C			Phthalic Anhydride	X	X	A	X	X		A	A	C	A	A	B	B	A
Oxychloride Alum	A	A	A	A	A	A		X									Pickle Brine	A	A		A	A	A								
Oxygen Gas	A	A	A	A	A	A	A	A	C	A	A	A					Pickling Solutions	A	A	A	A	A	A	C	B	X					
Ozone	B	C	B	B	A	A	A	A	X	A	A	A					Picric Acid	C	A	A	X	X	A	C	A	B	B	X	AB	A	B
Palmitic Acid 10%	A	A	A	A	A	A	B	A	A								Plating Solutions, Antimony	A	A	A	A	A	A	A	A	A	A	A	A	A	
Palmitic Acid 70%	A	A	A	X		B	A	A									Plating Solutions, Arsenic	A	A		A	A	A	A	A	A	A	A	A	A	
Paraffin	A	A	A	A	A	A	X	B	A	A	A	A	A	A			Plating Solutions, Brass	A	A	A	A	A	A	A	A	A	A	A	A	A	
Pentane		A			X	A	A	A	A	A	C						Plating Solutions, Bronze	A	A	A	A	A	A	A	A	A	A	A	A	A	

A = Excellent, no effect • B = Good, minor effect • C = Fair, data not conclusive, testing recommended • X = Not recommended.

Ratings are based on testing at an ambient temperature of 70°F. The chemical resistance table is for reference only. End users should test to determine application suitability. Butterfly valves, Solenoid valves, Diaphragm valves and all other valves with elastomers fully exposed to process media should derate elastomer scores by one level (i.e. "B" becomes "C", "C" becomes "X").

# Chemical Resistance Guide, CONTINUED

CHEMICALS	CPVC	PP	PTFE	PVC	PVC-GF (Fibertec™)	PVDF	Ultram® (GF 40%)	EPDM	FPM	Nitrile (Buna N)	Hastelloy® C	Monel®	18-8 SS	316 SS	416 SS	Titanium	CHEMICALS	CPVC	PP	PTFE	PVC	PVC-GF (Fibertec™)	PVDF	Ultram® (GF 40%)	EPDM	FPM	Nitrile (Buna N)	Hastelloy® C	Monel®	18-8 SS	316 SS	416 SS	Titanium
Plating Solutions, Cadmium	A	C	A	A	A	A	A	A	A	A	A	A	A	A	A	A	Potassium Perborate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Plating Solutions, Chrome	A	C	A	A	A	A	B	C	X	X	C	C	A	A	C	C	Potassium Perchlorate	A	A	A	A	A	A	A	A	A	A	B	C	B	AC	AC	B
Plating Solutions, Copper	A	A	A	A	A	A	A	A	A	A	A	X	A	C	C	C	Potassium Permanganate	A	B	A	A	A	A	A	A	A	A	B	C	B	AC	AC	B
Plating Solutions, Gold	A	C	A	A	A	A	A	A	A	A	A	C	A	C	18-8 SS	316 SS	Potassium Persulfate	A	A	A	A	A	A	A	A	A	A	A	A	X			
Plating Solutions, Iron	A	C	A	X	X			A	A	A		C	A	C	416 SS		Potassium Phosphate	A										A					
Plating Solutions, Lead	A	A	A	A	A	A	A	A	B	A	A	C	X	Potassium Salts	A	A									A	A							
Plating Solutions, Indium	A	A	A	A	A			A	A		C	A	Potassium Sulfate	A	A	A	A	A	A	A	A	A	A	A	A	A	AB	B	B				
Plating Solutions, Nickel	A	A	A	A	A	A	A	A	A	A	C	A	Potassium Sulfide	A	A	A	A	A	A	A	A	A	A	A	AB	A	B	B					
Plating Solutions, Rhodium	A	A	A	A	A	A	A	A	A	A	X	X	Potassium Thiosulfate	A										A	A								
Plating Solutions, Silver	A	A	A	A	A	A	A	A	A	A	A	A	Potassium Bicarbonate	A	A	A	A	A	A	A	A	A	A	A	A	A	B	B	A				
Plating Solutions, Tin	A	A	A	A	A	A	A	A	B	A	A	C	X	Propane	A	B	A	A	A	A	X	A	A	A	A	A	A	A	A	A			
Plating Solutions, Zinc	A	A	A	A	A	A	A	A	A	A	X	A	Propargyl Alcohol	A	A	A	A	A	A														
Polyethylene Glycol	A	A	A	A	A	A	A	A	A	A			Propyl Acetate		A					B	X	X	A										
Polyvinyl Acetate Emul		A		A	A	A		A	A				Propyl Alcohol (Propanol)	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A				
Polyvinyl Alcohol	X	A	A	A	A	A	A	A	A				Propylene Dichloride	X	C	A	X	X	A	X	B	X	A	C									
Potash	A	A	A	A	A	A	B	C	C		A		Propylene Glycol	C	A				A	A	A	B	B	AB	A								
Potassium Acetate	A	A	A	A	A	A	A	X	B	A	C		Propylene		A				X	A	X		A										
Potassium Alum	A	A	A	A	A	A	A	A	A	A		X	Pyridine	X	C	B	X	X	C	X	X	A	A	B	C	B							
Potassium Bichromate	A	A	A	A	A	A	A	A	A	A	AC	AB	Pyrogallic Acid		A	B	C	X		A	A	AB	AB	AB	A	B							
Potassium Bisulfate	A	A	A	A	A	A	A	A	A	A	A	A	Rayon Coagulating Bath	A	A	A	A	A	A														
Potassium Bromate	A	A	A	A	A	A	A	A	A	A	A	A	Rhodan Salts	A	A	A	A	A	A	A	A	A											
Potassium Bromide	A	A	A	A	A	A	A	A	A	A	A	AC	B	Rosins		A	A				A	A				A	B						
Potassium Carbonate	A	A	A	A	A	A	A	A	B	AB	A	AB	A	B	A	Rum	A	A	A	A	A	A	B	A									
Potassium Chlorate	A	A	A	A	A	A	A	A	A	A	AC	AB	A	B	A	Rust Inhibitors	A						A	A				A					
Potassium Chloride	A	A	A	A	A	A	A	A	A	A	AB	C	A	B	A	Salad Dressings	A	A	A	A	A	A	A	A									
Potassium Chromate	A	A	A	A	A	A	A	A	A	A	A	A	Salicylaldehyde		A	X	X	C	X	A	A												
Potassium Coppercyanide	A	A	A	A	A	A	A	A	A				Salicylic Acid		A	A	A	A	A	A	A	C	A	AB	A	B							
Potassium Cyanide	A	A	A	A	A	A	A	B	A	B	B	AC	B	Saline Solutions	A	A																	
Potassium Dichromate	A	A	A	A	A	A	A	A	A	A			Salt Brine	A	A	A	A	A	A	A	A	A	A	A	A	A							
Potassium Ferricyanide	A	A	A	A	A	A	A	A	A	A	BC	AC	A	B	A	Sea Water	A	A	A	A	A	A	B	AB	C	C	A						
Potassium Ferrocyanide	A	A	A	A	A	A	A	A	C	B	AC	B	A		Selenic Acid	A	A	A	A	A	A												
Potassium Fluoride	A	A	A	A	A	A	A	A	A	A	A	A	Sewage	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A				
Potassium Hydroxide 25%	A							A			A	A		Shellac Orange	A	A																	
Potassium Hydroxide 50%	A	A		A	A	B				A	A	A		Shellac Bleached	A	A																	
Potassium Hydroxide	A	A	A	A	A	A	B	C	C	AB	A	A	C	B	C	Silicic Acid	A	A	A	A	A	A	A	A									
Potassium Hypochlorite	A	A	A	A	A	A	A	A	X	B	X	X	X		Silicone Oil	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A		
Potassium Iodide	A	A	A	A	A	A	A	A	A	A	AB	A	A	A		Silver Bromide																	
Potassium Nitrate	A	A	A	A	A	A	A	B	A	AB	A	B	B	A		Silver Cyanide	A	A	A	A	A	A	A	A	AB	A	A	A					

A = Excellent, no effect • B = Good, minor effect • C = Fair, data not conclusive, testing recommended • X = Not recommended.

Ratings are based on testing at an ambient temperature of 70°F. The chemical resistance table is for reference only. End users should test to determine application suitability.

Butterfly valves, Solenoid valves, Diaphragm valves and all other valves with elastomers fully exposed to process media should derate elastomer scores by one level (i.e. "B" becomes "C", "C" becomes "X").



# HAYWARD®

## Chemical Resistance Guide, CONTINUED

CHEMICALS	CPVC	PP	PTFE	PIPC	PIPC-GF(Fiberloc™)	PVDF	UHMW® (GF 40%)	EPDM	FPM	Nitrile (Buna N)	Hastelloy® C	Monel®	18-8 SS	316L SS	410 SS	Titanium	CHEMICALS	CPVC	PP	PTFE	PIPC	PIPC-GF(Fiberloc™)	PVDF	UHMW® (GF 40%)	EPDM	FPM	Nitrile (Buna N)	Hastelloy® C	Monel®	18-8 SS	316L SS	410 SS	Titanium
Silver Nitrate	A	A	A	A	A	A	C	A	C	AB	X	B	B	B	A	Sodium Nitrate	A	A	A	A	A	A	A	A	B	C	AB	B	A	B	B	A	
Silver Salts	A	A	A	A	A	A	A	A	A							Sodium Nitrite	A	A	A	A	A	A	A	A	A	AC	BC	A	B				
Silver Sulfate	A	A	A	A	A	A	A	A	C							Sodium Palmitrate	A	A	A	A	A	A	A										
Soap Solutions	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	Sodium Perborate	A	A	A	A	A	A	A	A	A	C	A	A	AB	C	B		
Soda Ash		A						A	A	A						Sodium Perchlorate	A	A	A	A	A	A	A										
Sodium Acetate	A	A	A	A	A	A	A	C	C	A	A	AB	B	B	A	Sodium Peroxide	A	A	A	A	A	A	A		B	A	C	AB	AC	A	A	A	
Sodium Aluminate	A	A	A	A	A	A	A	A	A	AB	AB	AB	A	C	B	Sodium Phosphate Acid	A	A	A	A	A	A	A	A	A	A	A	A	B				
Sodium Benzoate	A	A	A	A	A	A				A	AB					Sodium Phosphate Alkaline	A	A	A	A	A	A	A	A	A	A	A	A	A				
Sodium Bicarbonate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	Sodium Phosphate Neutral	A	A	A	A	A	A	A	A	A	A	A	A	AB	AC			
Sodium Bichromate	A	A	A	A	A	A	A	A	B		AC		B			Sodium Polyphosphate		A							A	A	B			A	A		
Sodium Bisulfate	A	A	A	A	A	A	A	A	B	B	AB	X	A	A	A	Sodium Silicate	A	A		A	A	A	A	A	A	A	A	A	A	AB	B	B	A
Sodium Bisulfite	A	A	A	A	A	A	A	A	A	B	B	C	A	C	A	Sodium Sulfate	A	A	A	A	A	A	A	A	A	A	A	A	A	B	B	A	
Sodium Borate	A	A	A	C	C	A	A	A	A	AB	A	A				Sodium Sulfide	A	A	A	A	A	A	A	A	A	C	A	AB	AC	B	X	A	
Sodium Bromide	A	A	A	A	A	A	A	A		AB	AC	A		C		Sodium Sulfite	A	A	A	A	A	A	A	A	A	A	A	B	A	C	B	A	
Sodium Carbonate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	Sodium Tetraborate		A							A	A	A	AB	A	A	A		
Sodium Chlorate	A	A	A	A	A	A	A	A	C	C	A	X	BC	B	B	Sodium Thiocyanate	A	A	A	A	A	A	A	A	A	A							
Sodium Chloride	A	A	A	A	A	A	A	A	A	A	A	A	C	B	A	Sodium Thiosulfate	A	A	A	A	A	A	A	A	A	B	A	AB	A	A	A		
Sodium Chlorite	X	X	B	X	X		X	X								Sodium	A	A	A	A	A	A	A	A	A								
Sodium Chromate	A	A	A						B	A	A	AB	AC	A	B	Sorghum									A	A			A				
Sodium Cyanide	A	A	A	A	A	A	A	A	A	A	X	A	A	A	A	Soy Sauce									A	A			A				
Sodium Dichromate	A	A	A	A	A	A	A	A	A							Soybean Oil	A	A	A	A	A	A	A	A	A	A	A	AB	A				
Sodium Ferricyanide	A	A	A	A	A	A	A	A	A		AC	C		B		Stannic Chloride	A	A	A	A	A	A	A	A	A	A	AB	X	X	A	X	A	
Sodium Ferrocyanide	A	A	A	A	A	A	A	A	A		A	A				Stannic Salts	A	A	A	A	A	A	A	A	A								
Sodium Fluoride	A	A	A	A	A	A	A	B	B	C	A	A	B		C	Stannous Chloride	A	A	A	A	A	A	B	B	C	B	C	X	C	C	A		
Sodium Hydrosulfide												A	A			Starch	A	A	A	A	A	A	A	A	A	A	A	AB	A				
Sodium Hydrosulfite			A	C					A	A	A					Stearic Acid	A	B	A	A	A	A	C	A	B	A	A	B	B	A			
Sodium Hydroxide 15%	A	A	A	A	A	A	A	A	C	A	A		B	B	A	Stoddard Solvent	X	C	A	X	X	A	X	A	B	A	A	A	A	A	A		
Sodium Hydroxide 20%	A	A	A	A	A	A	A	A	C	A	A		B	B	A	Styrene		A			A		X	C	X		AC	A	A				
Sodium Hydroxide 30%	A	A	A	A	A	A	A	C	A			B	B			Succinic Acid	A	A	A	A	A	A	A	A	A	A	AC	B					
Sodium Hydroxide 50%	A	A	A	A	A	A	A	C	X	A		B	C	A		Sugar Solutions	A	A	A						A	A							
Sodium Hydroxide 70%	A	B	A	A	A	B	A	X	X	A			X	A		Sulfamic Acid	X	X	X	X	X				B								
Sodium Hydroxide Conc	A	A	A	A	A	A	A	B	X	A	AB	A	C			Sulfate Liquors	A	A		A	A	A	A	A	A	A	A	B	X	C	A		
Sodium Hypochlorite 20%	A	C	A	A	A	A	X	A	C	A		C		A		Sulfated Detergents	A	A		A	A	A											
Sodium Hypochlorite 5% (Bleach)	A	C	A	A	A	A	B	A	X	AB	X	X	B	X	AC	Sulfite Liquor	A	A	A	A	A	A	A	A	B	A	C	C	X	X			
Sodium Hypochlorite	A	C	A	A	A	A	X	X	X	AB	X	X	X	X		Sulfur 10%	A	A	A	A	A	A	X	A	C	A	A	C	A				
Sodium Hyposulfite														A		Sulfur Chloride	A	C	A	A	A	A	X	A	X	A	C	X	X	C			
Sodium Metaphosphate	A	C	A	A	A	A	A	A	A	A	A	A	A	A	A	Sulfur Dioxide Dry	A	A	A	A	A	A	A	A	X	B	A	B	B				
Sodium Metasilicate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	Sulfur Dioxide Wet	A	A	A	X	X	A	A	A	X	AC	X	A	B	B			

A = Excellent, no effect • B = Good, minor effect • C = Fair, data not conclusive, testing recommended • X = Not recommended.

Ratings are based on testing at an ambient temperature of 70°F. The chemical resistance table is for reference only. End users should test to determine application suitability.

Butterfly valves, Solenoid valves, Diaphragm valves and all other valves with elastomers fully exposed to process media should derate elastomer scores by one level (i.e. "B" becomes "C", "C" becomes "X").

# Chemical Resistance Guide, CONTINUED

CHEMICALS	CPVC	PP	PTFE	PVC	PVC-GF	Fibertec®	PVDF	Ultram® (GF 40%)	EPDM	FPM	Nitrile/Buna N	Hastelloy® C	Monel®	18-8 SS	316 SS	416 SS	Titanium	CHEMICALS	CPVC	PP	PTFE	PVC	PVC-GF	Fibertec®	PVDF	Ultram® (GF 40%)	EPDM	FPM	Nitrile/Buna N	Hastelloy® C	Monel®	18-8 SS	316 SS	416 SS	Titanium
Sulfur Dioxide	X	A	X	C			A	C	X			A	A					Trichloroacetic Acid	A	C	A	A	A	A		X	X	X	A	BC	X	X	X		
Sulfur Slurries	A	A		A	A	A												Trichloroethane			A	X		X	X	A	X	A	C		A			A	
Sulfur Trioxide Dry	C	X	B	C	C	X	C	C	C		AB	A	C	B				Trichloroethylene	X	B	A	X	X	A	X	X	A	C	A	B	A	A	A	B	
Sulfur	A	X	A	A	A	A	C	A	C	A	BC		A				Trichloropropane		A	X						A	A	A	A	A	A	A			
Sulfuric Acid 10%	A	A	A	A	A	A	A	B	A	C			C	X	A		Tricresyl Phosphate		A	X	X				A	B	X	A		A	A		B		
Sulfuric Acid 100%	A	X	B	X	X	C	X	C	X				C	C	X		Triethanolamine	C		B	C	C			A	X		A	A	A					
Sulfuric Acid 30%	A	A	A	A	A	A	A	A	A	C			X	X	C		Triethyl Phosphate	A	A	A	A	A	C	A	A								A		
Sulfuric Acid 50%	A	A	A	A	A	A	B	A	C				X	X	C		Triethylamine	A	X		A	A	C	A		A	A								
Sulfuric Acid 60%	A	A	A	A	A	B	B	A	X				X	X	C		Trimethylpropane	A	A	A	A	A	A												
Sulfuric Acid 70%	A	C	A	A	A	A	A	A	A	C			X	X	C		Trisodium Phosphate	A	A	A	A	A	A			A	A	A					A		
Sulfuric Acid 80%	A	A	A	X	X	A	A	A	C				X	X	X		Turbine Oil	A	B	A	A	A			X	A	B		A						
Sulfuric Acid 90%	A	C	A	X	X	A	A	A	C				X	X	X		Turpentine	A	B	A	X		A	A	C	A	C	A	AB	AB	A	B			
Sulfuric Acid 95%	A	X	A	X	X	A	X	X	A	X			X	X	X		Urea	A	A	A	A	A	A	A	A	A	C	A							
Sulfuric Acid 98%	A	X	B	X	X	A	X	X							X	X	Urine	A	A	A	A	A	A		A	A	A		A	A					
Sulfurous Acid	A	A	A	A	A	A	C	A	X	B	BC	B	C	A			Vanilla Extract	A	A		A														
Sulfuryl Chloride		A	A														Varnish	A	A			A			X	A	B	A	A	A	A				
Syrup		A	A	A	A				A	A							Vaseline	A	A	A	X	X	A		X	A	A	A	A						
Tall Oil	A	A	A	A	A	A	X	A	A	A	A	C			X		Vegetable Oil	C	A	A	A	A	A		A	A	A	A	A	A					
Tallow		A	A		A		A	A	A	B	A	A					Vinegar	A	A	A	A	A	A	A	A	A	C	A	A	A	A	A	A		
Tannic Acid	A	A	A	A	A	A	B	A	C	A	A	AC	C	B	A		Vinyl Acetate	X	A	X	X	A	X	B	X	X	A		AC						
Tanning Liquors	A	A	A	A	A	A	B	A	C	A			A	A			Vinyl Chloride		A					C	A	X	A	B	B	A					
Tar	X	B	A	X	X	A	X	A	C	A	A	A	B				Vinyl Ether		A					X	B										
Tartaric Acid	A	A	A	A	A	A	B	A	C	A	A	B	B	A			Water Potable	A	A	A	A	A	A		A	A	A	A	A	A	A				
Tertiary Butyl Alcohol	A	A	A	A	A	A	B	A									Water Salt	A	A	A	A	A	A		A	A	A	B	AB	A	C				
Tetrachlorethane		A	A	X	X		X	A	X	A	A	AB	A		A		Water Sewage	A	A	A	A	A	A		A	A	A								
Tetrachloroethane		A		X	A		X	A			A	A	A				Water, Acid Mine	A	A	A	A	A	A		A	A	A					A	C		
Tetraethyl Lead	A	A	A	B	C	A	X	B	C		A						Water, Deionized	A	A	A	A	A	A		A	B	A	A	A	A	A				
Tetrahydrofuron	X	B	A	X	X	B	X	X	X	X	A	B		A			Water, Demineralized	A	A		A	A	A		A	A	A	A	A						
Tetralin	X	X	A	X	X	A	X	A	X								Water, Distilled	A	A	A	A	A	A		A	A	A	A	A	A	A				
Thionylchloride	X	X	A	X	X	X											Weed Killers								A	B			A						
Thread Cutting Oils	A	A		A	A	A	X		A								Whey								A	A			A						
Titanium Tetrachloride	X	X	A	X	X	X	X	A	C	A	B	A					Whiskey	A	A	A	A	A	A		A	A	A	AB	A	A					
Titanous Sulfate	A	A	A	A	A	A											White Acid		A			A													
Toluene (Toluol)	X	C	A	X	X	B	C	X	C	X	A	A	A	A	A		White Liquor	A	A	A	A	A	A		A	A	B	A	A	A					
Tomato Juice	A	C	A	A	A	A	A	A	A	AB	A	A	C				Wines	A	A	A	A	A	A		A	A	A	AB	A	A	C				
Toxaphene-Xylene	X	X		X	X	A											Xenon		A						A	A	A		A						
Transformer Oil	A	A	A	A	A	A	X	A	A	A	A	A	A				Xylene	X	X	A	X	X	A	X	X	B	X	A	A	A	A				
Tributyl Phosphate	X	C	A	X	X	A	A	X	X								Xylol	X	X	A	X	X	A		X	A	C								

A = Excellent, no effect • B = Good, minor effect • C = Fair, data not conclusive, testing recommended • X = Not recommended.

Ratings are based on testing at an ambient temperature of 70°F. The chemical resistance table is for reference only. End users should test to determine application suitability.  
Butterfly valves, Solenoid valves, Diaphragm valves and all other valves with elastomers fully exposed to process media should derate elastomer scores by one level (i.e. "B" becomes "C", "C" becomes "X").



## Chemical Resistance Guide, CONTINUED

CHEMICALS	CPVC	PP	PTFE	PVC	PVC-GF/Fiberloc™	PVDF	Ultem® (GF-40%)	EPDM	FPM	Nitrile (Buna N)	Hastelloy® C	Monel®	18-8 SS	316 SS	416 SS	Titanium
Yeast	A	A		A		A	A									
Zeolite		A					A	A	B							
Zinc Acetate	A	A	A	A	A	A	A	C	B	A						
Zinc Carbonate	A	A						A	A	B	B	C		B		
Zinc Chloride	A	A	A	A	A	A	A	A	A	B	X	B	C	A		
Zinc Chromate		A														
Zinc Nitrate	A	A	A	A	A	A	A	A								
Zinc Salts		A	A	A	A		A	A	A							
Zinc Sulfate	A	A	A	A	A	A	A	A	A	A	B	A	A	A		
Zirilite			A				A	C	B							

A = Excellent, no effect • B = Good, minor effect • C = Fair, data not conclusive, testing recommended • X = Not recommended.

Ratings are based on testing at an ambient temperature of 70°F. The chemical resistance table is for reference only. End users should test to determine application suitability.  
Butterfly valves, Solenoid valves, Diaphragm valves and all other valves with elastomers fully exposed to process media should derate elastomer scores by one level (i.e. "B" becomes "C", "C" becomes "X").